



514, 6th Floor, Adamji Bldg., 413, Narshi Natha Street, Mumbai - 400 009. (INDIA).

Tel. : 0091-22-2343 9093 | Fax : 0091-22-6634 9992 | E-mail : info@hajexports.com | Web : www.hajexports.com

TECHNICAL DATA SHEET

HMCH-P – VINYL COPOLYMER RESIN

HMCH-P IS VINYLACRYLATE RESIN FULLY SOLUBLE IN ETHYL ACETATE (EA) AND EXHIBITS LOW SOLUTION VISCOSITY. HMCH-P IS SPECIALLY MADE FOR HIGH SOLIDS HSL AND IS USED WHERE THERE IS REQUIREMENT OF HIGH BOND STRENGTH.

<u>POLYMER COMPOSITION % BY WT.</u>	
VCI	61
VAC	9
MALEIC ACID	3
MMA/N-BMA	27
APPEARANCE	WHITE POWDER
REACTIVE FUNCTIONALITY	ACID
ACID NO.	4.5
GLASS TRANSITION TEMP. °C	58
VISCOSITY @ 25°C, SOL IN EA B4 CUP (IN SEC)	32